

AMENDMENT TO CLAIMS

This version of claims will replace all prior versions and listings of claims.

1. (Previously amended) A coating formulation for a reactive dye layer for a limited-play optical storage medium, said formulation comprising:

- (a) at least one polymeric polyhydroxy compound selected from the group consisting of branched polyhydroxystyrene homopolymers, polyhydroxystyrene copolymers prepared by polymerizing a 4-hydroxystyrene derivative with at least one olefin co-monomer, and cellulose derivatives;
- (b) at least one polymeric carrier selected from the group consisting of thermoplastic acrylic polymers, polyester resins, epoxy resins, polythiolenes, UV curable organic resins, polyurethanes, thermosettable acrylic polymers, alkyds, vinyl resins, and combinations thereof; and
- (c) at least one reactive material selected from the group consisting of oxygen sensitive leuco methylene blue, brilliant cresyl blue, basic blue 3, toluidine 0, combinations comprising at least one of the foregoing reactive materials, and protected forms of any of the foregoing reactive materials.

2. (Previously cancelled)

3. (Cancelled)

4. (Original) The coating formulation in accordance with claim 3 wherein said olefin co-monomer is selected from the group consisting of methyl methacrylate, 2-hydroxyethyl methacrylate, methyl acrylate, ethyl acrylate, dimethyl fumarate, dimethyl maleate, maleic anhydride, acrylonitrile, butadiene, isoprene, styrene, ethylene, and tetrafluoroethylene.

5. (Previously amended) The coating formulation in accordance with claim 1 wherein said polyhydroxystyrene copolymer is a poly(hydroxystyrene-co-methyl methacrylate).

6. (Previously Cancelled)

7. (Previously amended) The coating formulation in accordance with claim 1 wherein said cellulose derivative is selected from the group consisting of cellulose, cellulose acetate, cellulose acetate butyrate, cellulose propionate, cellulose triacetate, ethyl cellulose, hydroxybutyl methyl cellulose, hydroxypropyl cellulose, hydroxypropyl methyl cellulose, and methyl cellulose.

8. (Previously cancelled)

9. (Original) The coating formulation in accordance with claim 1, wherein said carrier comprises poly(methyl methacrylate) and said reactive material comprises leuco methylene blue.

10. (Original) The coating formulation in accordance with claim 1, wherein said reactive material is present in an amount corresponding to between about 1 weight % and about 10 weight %, based upon a total weight of said coating formulation.

11. (Original) The coating formulation in accordance with claim 10, wherein said reactive material is present in an amount corresponding to between about 4 weight % and about 7 weight %, based upon the total weight of said coating formulation.

12. (Original) The coating formulation in accordance with claim 11, wherein said reactive material is present in an amount corresponding to between about 4 weight % and about 6 weight %, based upon the total weight of said coating formulation.

13. (Previously cancelled)

14. (Previously amended) The coating formulation in accordance with claim 1, wherein said carrier comprises a thermoplastic acrylic polymer.

15. (Original) The coating formulation in accordance with claim 14, wherein said thermoplastic acrylic polymer comprises poly(methyl methacrylate/methacrylic acid).

16. (Original) The coating formulation in accordance with claim 1, wherein said carrier has an inherent viscosity less than about $0.300 \text{ cm}^3 \text{ g}^{-1}$.

17. (Original) The coating formulation in accordance with claim 16, wherein said carrier has an inherent viscosity less than about $0.250 \text{ cm}^3 \text{ g}^{-1}$.

18. (Original) The coating formulation in accordance with claim 17, wherein said carrier has an inherent viscosity less than about $0.200 \text{ cm}^3 \text{ g}^{-1}$.

19. (Original) The coating formulation in accordance with claim 1, wherein said polymeric polyhydroxy compound is present in an amount corresponding to between about 1 weight % and about 20 weight %, based upon the total weight of said formulation.

20. (Original) The coating formulation in accordance with claim 19, wherein said polymeric polyhydroxy compound is present in a range between about 3 weight % and about 15 weight %, based upon the total weight of said coating formulation.

21. (Original) The coating formulation in accordance with claim 20, wherein said polymeric polyhydroxy compound is present in a range between about 5 weight % and about 10 weight %, based upon the total weight of said coating formulation.

22. (Original) A coating formulation for a reactive dye layer for a limited-play optical storage medium, said formulation comprising:

- (a) a polyhydroxystyrene homopolymer;
- (b) a carrier comprising poly(methyl methacrylate/methacrylic acid) having an inherent viscosity of less than about $0.200 \text{ cm}^3 \text{ g}^{-1}$, and polymethylmethacrylate; and
- (c) a reactive material comprising N-(triisopropylsilyloxycarbonyl) leuco methylene blue;

said polyhydroxystyrene homopolymer being present in an amount corresponding to between about 5 weight % and about 10 weight % of a total weight of the reactive layer.

23. (Previously amended) A limited play optical storage medium for data, comprising:

- a) a first optically transparent substrate;
- b) a reflective layer;
- c) a data layer disposed between said substrate and said reflective layer;
- d) a reactive layer comprising
 - (i) at least one polymeric polyhydroxy compound selected from the group consisting of branched polyhydroxystyrene homopolymers, polyhydroxystyrene copolymers prepared by polymerizing a 4-hydroxystyrene derivative with at least one olefin co-monomer, and cellulose derivatives,
 - (ii) at least one polymeric carrier selected from the group consisting of thermoplastic acrylic polymers, polyester resins, epoxy resins, polythiolenes,

UV curable organic resins, polyurethanes, thermosettable acrylic polymers, alkyds, vinyl resins, and combinations thereof, and

(iii) at least one reactive material ; and

e) a second substrate.

24. (Previously amended) The limited play optical storage medium in accordance with claim 23, wherein said polymeric polyhydroxy compound comprises a branched polyhydroxystyrene homopolymer.

25. (Original) The limited play optical storage medium in accordance with claim 23, wherein said polymeric polyhydroxy compound comprises poly(hydroxystyrene-co-methyl methacrylate).

26. (Original) The limited play optical storage medium in accordance with claim 23, wherein said first substrate is plastic.

27. (Original) The limited play optical storage medium in accordance with claim 26, wherein said plastic comprises at least one thermoplastic having a glass transition temperature of about 100°C or greater.

28. (Original) The limited play optical storage medium in accordance with claim 27, wherein said thermoplastic is selected from the group consisting of polyvinyl chloride, polyolefins, polyesters, polyamides, polysulfones, polyimides, polyetherimides, polyether sulfones, polyphenylene sulfides, polyether ketones, polyether ether ketones, ABS resins, polystyrenes, polybutadiene, polyacrylates, polyacrylonitrile, polyacetals, polycarbonates, polyphenylene ethers, ethylene-vinyl acetate copolymers, polyvinyl acetate, liquid crystal polymers, ethylene-tetrafluoroethylene copolymer, aromatic polyesters, polyvinyl fluoride,

polyvinylidene fluoride, polyvinylidene chloride, tetrafluoroethylene, and mixtures, copolymers, reaction products, and composites comprising at least one of the foregoing thermoplastics.

29. (Original) The limited play optical storage medium in accordance with claim 28, wherein said thermoplastic comprises polycarbonate.

30. (Original) The limited play optical storage medium in accordance with claim 23, wherein said reactive material is selected from the group consisting of oxygen sensitive leuco methylene blue, reduced forms of methylene blue, brilliant cresyl blue, basic blue 3, toluidine 0, and combinations comprising at least one of the foregoing reactive materials.

31. (Original) The limited play optical storage medium in accordance with claim 30, wherein said reactive layer further comprises poly(methyl methacrylate) and leuco methylene blue.

32. (Original) The limited play optical storage medium in accordance with claim 23, wherein said reactive material is present in a range between about 1 weight % and about 10 weight %, based upon a total weight of said reactive layer.

33. (Original) The limited play optical storage medium in accordance with claim 32, wherein said reactive material is present in a range between about 4 weight % and about 7 weight %, based upon the total weight of said reactive layer.

34. (Original) The limited play optical storage medium in accordance with claim 33, wherein said reactive material is present in a range between about 4 weight % and about 6 weight %, based upon the total weight of said reactive layer.

35. (Previously cancelled)

36. (Previously amended) The limited play optical storage medium in accordance with claim 23, wherein said carrier comprises a thermoplastic acrylic polymer.

37. (Original) The limited play optical storage medium in accordance with claim 36, wherein said thermoplastic acrylic polymer comprises poly(methyl methacrylate/methacrylic acid) copolymer.

38. (Original) The limited play optical storage medium in accordance with claim 23, wherein said carrier has an inherent viscosity less than about $0.300 \text{ cm}^3 \text{ g}^{-1}$.

39. (Original) The limited play optical storage medium in accordance with claim 38, wherein said carrier has an inherent viscosity less than about $0.250 \text{ cm}^3 \text{ g}^{-1}$.

40. (Original) The limited play optical storage medium in accordance with claim 39, wherein said carrier has an inherent viscosity less than about $0.200 \text{ cm}^3 \text{ g}^{-1}$.

41. (Original) The limited play optical storage medium in accordance with claim 23, wherein said polymeric polyhydroxy compound is present in an amount corresponding to between about 1 weight % and about 20 weight % of a total weight of the reactive layer.

42. (Original) The limited play optical storage medium in accordance with claim 41, wherein said polymeric polyhydroxy compound is present in an amount corresponding to between about 3 weight % and about 15 weight % of the total weight of the reactive layer.

43. (Original) The limited play optical storage medium in accordance with claim 42, wherein said polymeric polyhydroxy compound is present in an amount corresponding to between about 5 weight % and about 10 weight % of the total weight of the reactive layer.

44. (Original) The limited play optical storage medium in accordance with claim 23, wherein the reflective layer comprises a metal.

45. (Original) The limited play optical storage medium in accordance with claim 44, wherein the metal is selected from the group consisting of aluminum, silver, gold, titanium, alloys, or combinations thereof.

46. (Original) The limited play optical storage medium in accordance with claim 45, wherein the metal comprises aluminum.

47. (Original) A limited play optical storage medium for data, comprising:

- a) an optically transparent polycarbonate;
- b) a reflective layer;
- c) a data layer disposed between said substrate and said reflective layer;
- d) a second substrate; and
- e) a reactive layer disposed between said reflective layer and said second substrate, said reactive layer comprising a polyhydroxystyrene homopolymer; a poly(methyl methacrylate methacrylic acid) copolymer, polymethylmethacrylate homopolymer, and leuco methylene blue; said copolymer having an inherent viscosity of less than about $0.200 \text{ cm}^3 \text{ g}^{-1}$.

48. (Previously amended) An adhesive formulation for a reactive dye layer for a limited-play optical storage medium, said formulation comprising:

- a) at least one polymeric polyhydroxy compound selected from the group consisting of branched polyhydroxystyrene homopolymers, polyhydroxystyrene copolymers

prepared by polymerizing a 4-hydroxystyrene derivative with at least one olefin co-monomer, and cellulose derivatives;

b) at least one curable acrylate monomer; and

c) at least one reactive material.

49. (Previously cancelled)

50. (Previously cancelled)

51. (Previously amended) The adhesive formulation in accordance with claim 48 wherein said olefin co-monomer is selected from the group consisting of methyl methacrylate, 2-hydroxyethyl methacrylate, methyl acrylate, ethyl acrylate, dimethyl fumarate, dimethyl maleate, maleic anhydride, acrylonitrile, butadiene, isoprene, styrene, ethylene, and tetrafluoroethylene.

52. (Previously amended) The adhesive formulation in accordance with claim 48 wherein said polyhydroxystyrene copolymer is a poly(hydroxystyrene-co-methyl methacrylate).

53. (Previously cancelled)

54. (Previously amended) The adhesive formulation in accordance with claim 48 wherein said cellulose derivative is selected from the group consisting of cellulose, cellulose acetate, cellulose acetate butyrate, cellulose propionate, cellulose triacetate, ethyl cellulose, hydroxybutyl methyl cellulose, hydroxypropyl cellulose, hydroxypropyl methyl cellulose, and methyl cellulose.

55. (Original) The adhesive formulation in accordance with claim 48, wherein said reactive material selected from the group consisting of oxygen sensitive leuco methylene blue,

brilliant cresyl blue, basic blue 3, toluidine 0, combinations comprising at least one of the foregoing reactive materials, and protected forms of any of the foregoing reactive materials.

56. (Original) The adhesion formulation of claim 55 wherein said protected form is N-(triisopropylsilyloxycarbonyl) leuco methylene blue.

57. (Original) The adhesive formulation in accordance with claim 48, wherein said reactive material is present in an amount corresponding to between about 0.5 weight % and about 10 weight %, based upon a total weight of said adhesive formulation.

58. (Original) The adhesive formulation in accordance with claim 57, wherein said reactive material is present in an amount corresponding to between about 1 weight % and about 7 weight %, based upon the total weight of said adhesive formulation.

59. (Original) The adhesive formulation in accordance with claim 58, wherein said reactive material is present in an amount corresponding to between about 1 weight % and about 4 weight %, based upon the total weight of said adhesive formulation.

60. (Original) The adhesive formulation in accordance with claim 48, wherein said curable acrylate monomer is selected from the group consisting of polyfunctional acrylates and monoacrylates.

61. (Original) The adhesive formulation in accordance with claim 60, wherein said polyfunctional acrylate comprises trimethylolpropane triacrylate, and said mono acrylate comprises phenoxyethyl acrylate.

62. (Original) The adhesive formulation in accordance with claim 61 further comprising Sn (II) 2-ethylhexanoate.

63. (Original) The adhesive formulation in accordance with claim 48 having a viscosity in a range between about 200 and about 600 cP at 25°C.

64. (Previously amended) A limited play optical storage medium for data, comprising:

- a) a first optically transparent substrate;
- b) a reflective layer;
- c) a data layer disposed between said substrate and said reflective layer;
- d) a reactive layer prepared from an adhesive formulation comprising
 - (i) at least one polymeric polyhydroxy compound selected from the group consisting of branched polyhydroxystyrene homopolymers, polyhydroxystyrene copolymers prepared by polymerizing a 4-hydroxystyrene derivative with at least one olefin comonomer, and cellulose derivatives;
 - (ii) at least one curable acrylate monomer; and
 - (iii) at least one reactive material; and
- a) a second substrate.

65. (Previously cancelled)